




KONGERIKET NORGE
The Kingdom of Norway

PCT/NO 99 / 0 0 1 1 6




5

Bekreftelse på patentsøknad nr

Certification of patent application no

1998 1631



► Det bekreftes herved at vedheftede dokument er nøyaktig utskrift/kopi av ovennevnte søknad, som opprinnelig inngitt 1998.04.08

► *It is hereby certified that the annexed document is a true copy of the above-mentioned application, as originally filed on 1998.04.08*

1999.04.19

Freddy Strømmen

Freddy Strømmen
Seksjonsleder

Mette E. Hansen

Mette E. Hansen



PATENTSTYRET
Styret for det industrielle rettsvern

TH/TK

Søknad om patent.

Søknadsskriv

08.APR98 981631

Til

Patentstyret
Boks 8160 Dep.
0033 Oslo

Utfylles av Styret

Behandlende medlem

Int. Cl⁸

C08F

KL

Søkers/fullmektigs referanse
(Angis hvis ønsket):

60848-TH

8. apr 98 622888

Aim.tilgj

11 OKT. 1998

P981631 1

1.000,00

Oppfinnelsens
benevnelse:Katalysator for polymerisasjon av etylen, og fremgangsmåte
for fremstilling av denne.Hvis søknaden er
en internasjonal søknad
som videreføres etter
patentlovens § 31:

Den internasjonale søknads nummer

Den internasjonale søknads inngivelsesdag

Søker:

Navn, bopel og adresse.
(Hvis patent søkes av flere.
Opplysning om hvem som skal
være bemyndiget til å motta
meddelelser fra Styret på vegne
av søkerne).

(Fortsett om nødvendig på neste side)

Borealis A/S

Lyngby Hovedgade 96, DK-2800 Lyngby, DK

Oppfinder:

Navn og (privat-) adresse.

(Fortsett om nødvendig på neste side)

Se neste side

Fullmektig:

Hvis søknad tidligere
er inngitt i eller
utenfor riket:

(Fortsett om nødvendig på neste side)

Tandbergs Patentkontor AS

Prioritet kreves fra dato..... sted nr.

Prioritet kreves fra dato..... sted nr.

Prioritet kreves fra dato..... sted nr.

Hvis avdelt søknad:

Den opprinnelige søknads nr.:.....og dennes inngivelsesdag

Hvis utskilt søknad:

Den opprinnelige søknads nr.:..... begjært inngivelsesdag

Deponert kultur av
mikroorganisme:☐ Søknaden omfatter kultur av mikroorganismeUtlevering av prøve av
kulturen:☐ Prøve av den deponerte kultur av mikroorganisme skal bare utleveres til en særlig sakkyndig,
jfr. patentlovens § 22 åttende ledd og patentforskriftenes § 38 første ledd

981631

Angivelse av tegnings-
figur som ønskes
publisert sammen med
sammendraget

Fig. nr.

POSTADRESSE
Boks 8160 Dep.
0033 OsloKONTORADRESSE
Københavnsgt. 10
OsloTELEFON
22 38 73 00TELEKS
19 152
nopat nTELEFAKS
22 38 73 01POSTGIRO
0808 5170709BANKGIRO
1600.40.39916

60848

TECHNICAL FIELD

The present invention relates to a supported chromium oxide catalyst, in particular a catalyst system comprising an inorganic support, a chromium oxide and a metallocene compound, and a method for the preparation of said catalyst system. The catalyst produces branched polyethylenes without the use of a copolymer, and the molecular weight can be controlled by feeding hydrogen.

10

BACKGROUND ART

To obtain linear polyolefins having desired properties, different catalyst systems in combinations with controlled polymerisation conditions are used. A typical supported chromium catalyst that is extensively used in commercial polymerisations of ethylene is formed by depositing a chromium compound onto a support, which is then oxidised. The oxidised catalyst precursor may be introduced as such into a polymerisation reactor, where it will be reduced in situ by the olefin monomers to its active catalytic state. It is also well known that oxidised chromium compounds may be prereduced by suitable reagents, such as hydrogen or carbon-monoxide (J.P. Hogan, J. Polym. Sci., PtA-1, 8, 2637 (1970), and references therein). The resulting chromium surface species are generally accepted to be highly reactive. A prereduced chromium-based catalyst will produce polyethylenes having a broad molecular weight distribution (MWD) and mainly long, straight chains. Such catalysts are not hydrogen-sensitive.

Another commercially important class of catalysts used to polymerise α -olefins are the cyclopentadienyl transition metal catalysts, usually termed metallocene catalysts. Metallocenes contacted with Lewis acids will give effective polymerisation catalysts that produce linear polyethylenes having a narrow molecular weight distribution (MWD). Such catalysts are sensitive to the presence of hydrogen.

By adding comonomers and optionally hydrogen during the catalysed polymerisation reactions the density and chain branching of the produced polymer can be controlled. In the prior art efforts have

been made to develop combined catalyst systems that produce short chain branched polyethylenes, without the addition of comonomers during the polymerisation reactions.

5 US Patent 4,735,931 discloses a catalyst system prepared by first depositing a chromium compound on a predominantly silica support, activating said catalyst in an oxygen-containing atmosphere and thereafter subjecting the thus activated composition to reduction with carbon monoxide. The resulting
10 chromium catalyst composition is then precontacted with a cocatalyst selected from trialkyl boron and dialkyl aluminium alkoxide compounds, preferably triethyl borane, and thereafter contacted with ethylene. When used in olefin polymerisations this catalyst provides in situ generation of comonomers, resulting in
15 tough, flexible, mainly pure polyethylene resins.

US Patent 5,032,651 teaches the use of catalyst mixtures of two transition metal catalysts. One of the catalysts comprises chromium oxide supported on an aluminophosphate, and the other
20 one comprises a β -stabilized tetrahydrocarbyl zirconium compound supported on an inorganic material. The catalysts may be premixed before use, or they may be fed separately to the reactor. Olefinic polymers exhibiting high environmental stress crack resistance (ESCR) are produced.

25

EP 206794 describes an olefin polymerisation catalyst comprising a support contacted with a Group 4b, 5b or 6b metallocene and an aluminoxane.

30 EP 088 562 discloses a modified polymerisation catalyst comprising a silica support with deposited chromium. Following oxidation in dry air, the chromium is modified by being contacted with a transition metal compound of Ti, V or Cr, preferably Ti. Only the use of bis-toluene titanium is exemplified, and the
35 obtained polyethylenes have a substantial degree of branching and a medium or broad molecular weight distribution.

US 3,378,536 discloses a process for the polymerisation of ethylene by the use of a two-component catalyst system consisting

of (a) a chromium compound deposited on e.g. silica, where the chromium being activated in an oxygen-containing gas at a high temperature and then reduced with CO; and (b) chromium or vanadium arene where the arene is an aromatic, optionally substituted C₆ ring. The two catalyst components are preferably fed separately to the polymerisation reactor.

It is well known to a person skilled in the art that the various processing techniques used in the manufacturing of final articles from polyethylene resins require polyethylene grades having specific rheological properties. For instance, in the extrusion blow moulding of containers polyethylenes having a broad MWD and long straight chains are typically used, while in film blowing lower density polyethylenes are preferred.


It is an object of the present invention to provide a novel catalyst system that produces a branched polyethylene from ethylene without any addition of comonomer during the polymerisation reaction. A further object is to control the polymerisation reaction to produce polyethylenes having a desired density and molecular weight. Another object is to obtain polyethylene resins suitable for use blow moulding and film blowing processing.

It has now been found that a catalyst system comprising a prereduced chromium on silica catalyst that have been contacted with a metallocene compound fulfils the requirements above. The novel catalyst system produces a branched low density polyethylene polymer without any added comonomer. The density and molecular weight (and hence the melt flow index) of the polymer can be controlled by the addition of hydrogen to the reactor.

DISCLOSURE OF INVENTION

The present invention thus provides a catalyst system for the polymerisation of ethylene, comprising chromium oxide supported on an inorganic support, wherein

- a) said support being a particulate inorganic oxide;
- b) the chromium of said chromium oxide being in a reduced oxidation state, and comprising
- c) a metallocene compound having the formula:



wherein Cp is an unsubstituted or substituted cyclopentadienyl compound, and R' and R'', independent of each other, are selected from the group comprising alkyls having 1 to 6 carbon atoms, unsubstituted or substituted benzyl, and phenoxy substituted with alkyls having 1 to 6 carbon atoms, and R' or R'' may be a halide.

The invention also provides a method for the preparation of the catalyst system above, comprising the steps of:

- 10 a) calcining a support being a particulate, inorganic oxide selected from the group comprising alumina, silica, titania, zirconia, magnesia, and combinations thereof,
- b) joining onto the surface of said support a chromium-organic compound to obtain a catalyst precursor,
- 15 c) subjecting said catalyst precursor to oxidising conditions to obtain the chromium in an oxidised state,
- d) subjecting said catalyst precursor to reducing conditions to obtain a prereduced catalyst, thus
- e) reducing the oxidised chromium to obtain the main part thereof
- 20 in a bivalent oxidation state,
- f) contacting said reduced catalyst with a metallocene compound having the formula:



wherein Cp is an unsubstituted or substituted cyclopentadienyl compound, and R' and R'', independent of each other, are selected from the group comprising alkyls having 1 to 6 carbon atoms, unsubstituted or substituted benzyl, and phenoxy substituted with alkyls having 1 to 6 carbon atoms, and R' or R'' may be a halide.

30 BEST MODES FOR CARRYING OUT THE INVENTION

The catalyst system of the present invention comprises a supported reduced chromium/silica catalyst contacted with a metallocene compound. In general, metallocenes based on zirconium, hafnium and titanium are preferred as metallocene catalysts. By metallocenes are meant compounds in which a metal atom or ion or complex ion is π -bonded by at least one ligand, e.g. by 1, 2 or 3 ligands or ligand components. The π -bonding ligands in such catalysts may be simple unsubstituted cyclopentadienyl rings, but preferably they will be optionally

substituted fused ring systems (e.g. indenyl ligands), substituted cyclopentadienyl rings, optionally substituted bridged bis-cyclopentadienyl ligands or optionally substituted bridged bis fused ring systems (e.g. bis indenyl ligands).

5

The catalyst support may be any oxide of metals from groups 2, 3, 4, 11, 12, 13 and 14 of the Periodic System of Elements. Preferred metal oxides are magnesia, alumina, titania, zirconia and silica. A particularly preferred catalyst support is silica. 10 Such a silica support must contain not less than 90% pure silica, with the remaining part may consisting of other oxides, such as oxides of aluminium, zirconium, titanium, magnesium and phosphor. The support should consist of particles having preferably a spherical or spheroidal shape and a size from about 10 μm to 15 150 μm , more preferably from 20 μm to 120 μm , and a particle size distribution from narrow to broad within said ranges.

The chromium compound to be impregnated onto the silica support may be an inorganic chromium compound, such as chromium nitrate 20 and chromium oxide, or an organic chromium compound, such as chromium acetate. Other chromium compounds are also useable. The chromium compound can be joined with the support in any way known in the art, such as by coprecipitation with the silica support or addition to a silica gel after its formation, or after that 25 it has been dried. A typical procedure of impregnation comprises the use of a water-soluble compound, or the use of an organochromium compound in an anhydrous hydrocarbon solution. The only precondition is that the chromium compound can be oxidized to a chromium oxide. The amount of chromium compound joined with the 30 inorganic support must be sufficient to obtain from 0.1% to 10%, preferably from 0.5% to 2.0%, by weight of chromium, calculated as metallic chromium based on the weight of the supported chromium catalyst. When the impregnation is finished any possible remaining solvent is removed to obtain a dry solid.

35

Such solid chromium oxide/silica catalyst precursors are also commercially available from a number of producers. A closer description of their preparation is therefore regarded as being superfluous.

The obtained catalyst precursor must be activated before use. This is done by calcination in dry air or another oxygen-containing gas at temperatures in the range from 400 to 950 °C, preferably from 550 to 800 °C, during a period from 10 minutes
 5 to 24 hours, preferably from 2 to 20 hours. The oxidised catalyst precursor is conventionally subjected to reduction, preferably with carbon monoxide or a mixture of carbon monoxide and an inert component, such as nitrogen or argon. The reduction is normally performed at a temperature within the range from 300 to 500 °C,
 10 preferably from 350 °C to 400 °C, during a period from 5 minutes to 48 hours, preferably from 1 to 10 hours. When the reduction is completed, the major part of the contained chromium should preferably be in a bivalent oxidation state. The final chromium catalyst particles should have a surface area from 200 to 600
 15 m²/g, more preferably from 300 to 550 m²/g, and a pore volume from 1 to 3 cm³/g. The chromium oxide/silica catalyst in a reduced state, either as a dry powder or as a slurry in a dry oxygen-free hydrocarbon solvent, e.g. an alkane, must be stored in an inert ambience.


20

The present invention is not restricted to any particular procedure for the preparation of the chromium oxide/silica catalyst, and other methods than those described here may also be applicable.

25

The obtained chromium oxide/silica catalyst is contacted with a cyclopentadienyl-zirconium compound, hereinafter termed "zir-conocene". Preferred zirconocenes can be represented by the simplified formula:

30



wherein Cp designates cyclopentadienyl groups selected from unsubstituted cyclopentadienyl; cyclopentadienyl substituted with radicals selected from the group comprising unsubstituted and substituted linear, branched, cyclic or partially cyclic alkyl
 35 radicals, and annelated cyclic radicals, containing 1 to 20 carbon atoms; unsubstituted and substituted monocyclic or polycyclic aryl radicals which optionally also may contain hetero atoms; and aralkyl radicals. The substituents on the cyclopentadienyl ring may also form annelated structures comprising one

or more fused benzene, naphthalene or cyclohexene rings, which optionally may contain hetero atoms. The substituents R' and R'', equal or different, are selected from the group comprising alkyls having 1 to 6 carbon atoms, unsubstituted or substituted benzyl, and phenoxy substituted with alkyls having 1 to 6 carbon atoms. Preferably, R' and R'' are independantly selected from the group comprising methyl, benzyl or fenoxymethyl, and any combination thereof. One or R' and R'' may also be a halide, preferably chloride.

10

A number of suitable metallocene compounds of the formula above are known in the art and have been recited in the literature. Particularly preferred metallocene compounds are embodied in the working examples.

15

Particularly good results are obtained when Cp represents cyclopentadienyl, and R' and R'' are the same and are benzyl or methyl.

The zirconocene compound is joined with the activated prereduced chromium oxide/silica catalyst most conveniently by dissolving the zirconocene in a solvent, e.g. toluene, and impregnate the chromium oxide/silica catalyst with this toluene solution. Eventually, the solvent is removed by evaporation, preferably in an inert atmosphere, whereupon the catalyst is ready for use.

25

The final catalyst will contain both zirconium and chromium, preferably in a molar ratio of zirconium to chromium in the range from 0.1:1 to not higher than 2:1. More preferably the catalyst contains zirconium and chromium in a molar ratio from 0.5:1 to 1:1.

30

Prior to polymerisation, the catalyst may optionally be prepolymerised with a minor amount of ethylene and/or an α -olefin in accordance with methods well known in the art, before being fed continuously to the polymerisation reactor.

35

Polymerisations can be performed in any conventional type of reactor, such as in a batch reactor or most preferably in a continuous reactor. The present catalysts are suitable for use

in all types of olefin polymerisations, including gas phase and suspension polymerisations. In general, polymerisations are performed at temperatures below 110 °C, and at a total pressure in the range from ambient to 50 bar. Hydrogen is used to control the molecular weight, and consequently the melt flow index, of the polymer, whereas the catalyst determines the short chain branching on the polyethylene backbone and hence the density of the polyethylene.

10 The general polymerisation parameters mentioned above are well known in the art and further details concerning ethylene polymerisations should be superfluous. Typical polymerisation conditions are presented in the examples below.

15 It is realized that the present catalyst system has its highest catalytic activity when the substituents R' and R" of the zirconocene compound are pure hydrocarbyl radicals, in the examples embodied as benzyl or methyl. A person skilled in the art will understand that similar hydrocarbyl compounds are expected to have the same effect and that such compounds are contemplated by the present invention. The catalysts of this invention provide substantially higher activities than the prior art chromium/silica catalysts. When the substituents R' and R" contain hetero atoms, such as O and Cl, the present catalysts will get a reduced activity, typically lower than the activity of a comparative prior art chromium/silica catalyst. Thus, the activities of the catalysts of the present invention will be at their highest when the metallocene component is a pure hydrocarbyl zirconocene.

30 The present catalysts will have an activity that varies with the molar ratio between zirconium and chromium in the final catalyst. When the contained amount of zirconium is higher than the amount of chromium, the catalyst will have a lower catalytic activity than a comparative prior art chromium/silica catalyst. The present catalysts have their highest activity when the molar ratio between zirconium and chromium is about 0.5:1. This indicates that only a minor amount of zirconocene is required to increase substantially the activity of a chromium/silica catalyst.

The catalytic activities of the present catalysts are also influenced by the concentration of hydrogen present in the polymerisation reactor. It has been found that an optimum level is about 1 bar of hydrogen.

5

The hydrogen level will also influence on the short chain branching of the produced polyethylenes. Analysis of polyethylenes polymerised with the present catalysts show that the obtained polymers have a higher amount of short chain branching
10 than polyethylenes produced with a prior art chromium/silica catalyst. In particular, the amount of ethyl branches will increase. A higher level of hydrogen will increase the amount of short chain branching, in particular when using a catalyst having a ratio Zr/Cr of 0.5. By adjusting this ratio, as well as the
15 hydrogen level inside the reactor, the morphology of the final resin can be controlled. Compared with the common used prior art chromium/silica catalysts, the catalysts of the present invention have a higher activity and will give a higher amount of short chain branching.

20

The present catalysts are preferably used to homopolymerise ethylene. However, it is also possible to use the present catalysts in copolymerisations of ethylene with a comonomer or a mixture of comonomers. Useful comonomers are all polymerisable
25 α -olefins having the general formula $\text{CH}_2=\text{CHR}$, wherein R is a hydrocarbon radical containing 1-18 carbon atoms, preferably 1-10 carbon atoms. Examples of particularly preferred α -olefins are propylene, 1-butene, 1-hexene, 4-methyl-1-pentene and 1-octene. However, the greatest achievements of the present catalysts are
30 in homopolymerisations of ethylene.

The produced polyethylenes will have a density from 910 to >960 kg/m^3 , and a melt index from 0.01 to above 100 g/10 min, preferably from 0.1 to 60 g/10 min (determined according to the method
35 of ASTM 1238), depending on the polymerisation conditions, as explained above. More detailed specifications concerning the properties of the obtained polyethylenes are given in the examples.

EXAMPLES**Preparation of a Cr/SiO₂ catalyst**

A catalyst support of silica having a surface area of 300 m²/g and a pore volume of 1.6 cm³/g was impregnated with an aqueous solution of CrO₃ in an amount sufficient to finally obtain 1 % by weight of Cr, calculated as metal based on the weight of the support. The impregnated support was reduced at 380 °C in a gas consisting of 5% of CO in nitrogen for 4 h, and then allowed to cool to ambient temperature in an inert atmosphere. For further use, the obtained blue-coloured catalyst was suspended in a dry, oxygen-free, purified mineral oil to a level of about 10 % by weight of catalyst.

Synthesis of bis-cyclopentadienyl-zirconiumbenzyl (Cp₂ZrBz₂).

This zirconocene was prepared according to the method described by Fachinetti et al. in J. Chem. Soc., Chem. Commun., 1972, p. 654, by reacting 3 g of Cp₂ZrCl₂ with 20.6 ml of a 1.0 M solution of BzMgCl (Bz=benzyl) in toluene at 0 °C for 1.5 h. The obtained yellow product was recrystallized from a mixture of toluene/heptane at -25 °C. The crystallized solid was collected by filtration and dried in vacuum.

Synthesis of bis-cyclopentadienyl-zirconiummethyl (Cp₂ZrMe₂)

This zirconocene was synthesized according to the method described by Wailes et al. in J. Organomet. Chem., Vol. 34, 1972, p. 155, by reacting 5 g of Cp₂ZrCl₂ with 21.6 ml of MeLi (Me=methyl) in diethylether at 0 °C for 1 h. The precipitated LiCl was removed by filtration and the diethylether evaporated in vacuum to obtain a solid residue. This residue was heated at 80 °C and reduced pressure (2 to 10 torr). The obtained sublimed white crystalline Cp₂ZrMe₂ was collected.

Synthesis of bis-cyclopentadienyl-zirconiummethyl(fenoxymethyl) (Cp₂ZrMe(OPhMe))

To 4.84 ml of a 10% toluene solution of Cp₂ZrMe₂ was added a stoichiometric amount of a 2.1% toluene solution of cresol at ambient temperature and allowed to react for 1 h. Methane was released during the reaction.

Synthesis of bis-cyclopentadienyl-zirconiummethylchloride ($\text{Cp}_2\text{ZrMe}(\text{Cl})$)

To 10 g of a 5% solution of Cp_2ZrMe_2 , was added slowly 48.7 ml gaseous HCl at 0°C . The mixture was then allowed to reach
 5 ambient temperature and it was kept at this temperature overnight to complete the reaction.

General procedure for the preparation of zirconocene-containing catalysts

10 A synthesized zirconocene compound was contacted with the Cr/SiO_2 catalyst above. In an inert atmosphere at ambient temperature the zirconocene was added dropwise to a 10 % slurry of the Cr/SiO_2 catalyst and the reaction mixture stirred for at least 1 h to complete the reaction.

15

General polymerisation procedure

A 1 l laboratory stainless steel batch reactor equipped with a paddle stirrer was heated to a desired temperature between 90°C and 100°C and purged with nitrogen, then 1.5 ml of the catalyst
 20 slurry was introduced and a desired amount of hydrogen was fed to the reactor. Then 0.5 l of i-butane was added to act as a diluent, whereupon ethylene was introduced until a total pressure of 31.0 bar. The overall pressure was kept constant during the entire polymerisation run by feeding ethylene. The reactor
 25 temperature was kept constant at the fixed temperature to an accuracy of $\pm 0.5^\circ\text{C}$ by automatically adjusting the heating and/or cooling of the reactor. Polymerisation times were from 20 and 40 minutes.

30 Examples 1 to 8

These examples demonstrate the polymerisation of ethylene in the presence of a catalyst containing one of the various zirconocene compounds synthesised above. The examples show that the catalysts comprising Cr/SiO_2 contacted with Cp_2ZrBz_2 or Cp_2ZrMe_2 have the
 35 highest polymerisation activities. In all examples the molar ratio Zr/Cr equalled 1, the polymerisation temperature was in the range from 93°C to 98°C , and the H_2 pressure was either 1.0 or 0.5 bar. Polymerisation parameters and obtained results are given in table 1.

Examples 1 and 2

Polymerisation catalyst: Cr/SiO₂ contacted with Cp₂ZrBz₂.

In a 20 ml vial 0.510 g of the prepared Cr/SiO₂ catalyst (containing 1% Cr) was suspended in 4.168 g of mineral oil and
5 the bottle closed with a septum. By the use of a syringe 0.375 ml of a 10% toluene solution of Cp₂ZrBz₂ was added while stirring by the use of a magnet bar, and the stirring continued for 1 h more. The obtained catalyst was used in the polymerisation of ethylene according to the general polymerisation procedure
10 described above.

Examples 3 and 4

Polymerisation catalyst: Cr/SiO₂ contacted with Cp₂ZrMe₂.

The procedure of Examples 1 and 2 was followed, except that the
15 catalyst was prepared by adding 0.251 ml of a 10% solution of Cp₂ZrMe₂.

Examples 5 and 6

Polymerisation catalyst: Cr/SiO₂ contacted with Cp₂ZrMe(OPhMe).

20 The procedure of examples 1 and 2 was followed, except that the catalyst was prepared by adding 0.342 ml of a 10% solution of Cp₂ZrMe(OPhMe).

Examples 7 and 8

25 Polymerisation catalyst: Cr/SiO₂ contacted with Cp₂ZrMe(Cl).

The procedure of examples 1 and 2 was followed, except that the catalyst was prepared by adding 0.342 ml of a 5 % solution of Cp₂ZrMe(OPhMe).

30 **Example 9 (comparative example)**

Polymerisation catalyst: Cr/SiO₂.

The procedure of examples 1 and 2 was followed, except that the catalyst was prepared by suspending 2 g of the Cr/SiO₂ prepared above in 16.691 g of mineral oil in a 50 ml glass bottle which
35 was sealed with a septum. An amount of 1.5 ml of the catalyst slurry was withdrawn and used in a polymerisation run.

The results presented in Table 1 show that the pure hydrocarbyl zirconocenes of Examples 1 and 2, Cp_2ZrBz_2 , and 3 and 4, Cp_2ZrMe_2 , gave increased polymerisation activities compared with the standard prior art Cr/Si catalyst. On the other hand, the catalysts of Examples 5 and 6 containing hydrocarboxy substituents, and of Examples 7 and 8 containing chloride substituents, have lower activities than the prior art catalyst of Example 9. Further, the results show that the catalytic activity of the catalyst of Examples 1 and 2 depends on the hydrogen level present during polymerisation, and also properties like MFR and density of the produced polyethylene vary with the hydrogen concentration. Thus, the properties of the produced polyethylene can be controlled by regulating the hydrogen feed to the polymerisation reactor. The catalyst of Examples 3 and 4 shows the same tendency, but less pronounced. The activities of the catalysts of Examples 5 and 6, and 7 and 8, show a much less response to the presence of hydrogen.

20

25

30

35

TABLE 1
Polymerisation of ethylene in the presence of catalyst Cr/silica + Cp₂ZrR'R"

Ex.	R'	R"	Zr/Cr	H ₂ (bar)	Temp. (°C)	Activity g/g·h	MFR g/10 min	Density g/cm ³
Ex. 1	Bz	Bz	1	0.5	93	1054	0.09	0.933
Ex. 2	Bz	Bz	1	1.0	98	788	0.35	0.945
Ex. 3	Me	Me	1	0.5	93	1005	0.006	0.946
Ex. 4	Me	Me	1	1.0	94	849	0.017	0.947
Ex. 5	Me	OPhMe	1	0.5	93	338	0.004	0.952
Ex. 6	Me	OPhMe	1	1.0	97	341	0.03	0.952
Ex. 7	Me	Cl	1	0.5	93	383	0.01	0.950
Ex. 8	Me	Cl	1	1.0	97	392	0.05	0.047
Comp. 9	-	-	-	1.0	97	617	0.09	0.949

Examples 10 to 16

These examples demonstrate the relation between catalytic activity and the ratio Zr/Cr of the catalyst in the polymerisations of ethylene. The catalyst of Examples 1 and 2, Cp_2ZrBz_2 , and of Examples 3 and 4, Cp_2ZrMe_2 , were used. The general polymerisation procedure above was followed.

Example 10

Polymerisation catalyst: Cr/SiO₂ contacted with Cp_2ZrBz_2 , having a Zr/Cr molar ratio of 0.25:1.

The catalyst was prepared analogous to example 1 by suspending 1.750 g of prereduced 1% by weight Cr/SiO₂ in 14.685 g of mineral oil in a 50 ml glass bottle provided with a septum. To this mixture was added 0.352 ml of 10% by weight Cp_2ZrBz_2 in toluene, and the mixture was stirred for another 1 h. The obtained catalyst was then used in the polymerisation of ethylene.

Example 11

The polymerisation catalyst was prepared as in Example 10, except that 0.5 g of Cr/SiO₂ was suspended in 4.801 g of mineral oil in a 20 ml glass bottle, and 0.201 ml of a 10% by weight solution of Cp_2ZrBz_2 in toluene was added to obtain a Zr/Cr ratio of 0.5:1.

Example 12

The catalyst was prepared as in Example 11, except that 0.403 ml of a 10% by weight solution of Cp_2ZrBz_2 in toluene was added to obtain a Zr/Cr molar ratio of 1:1.

Example 13

The catalyst was prepared as in Example 11, except that 0.806 ml of a 10% by weight solution of Cp_2ZrBz_2 in toluene was added to obtain a Zr/Cr molar ratio of 2:1.

Example 14

Polymerisation catalyst: Cr/SiO₂ contacted with Cp_2ZrMe_2 , having a Zr/Cr molar ratio of 0.5:1.

The catalyst was prepared analogous to example 3 by suspending 1 g of Cr/SiO₂ in 8.327 g of mineral oil in a 50 ml glass bottle

provided with a septum. To this mixture was added 0.251 ml of a 10% by weight solution of Cp_2ZrMe_2 in toluene, and the mixture was stirred for another 1 h.

5 **Examples 15 and 16**

The catalyst was prepared as in Example 14, except using 0.502 ml and 1.004 ml of the 10% by weight solution of Cp_2ZrMe_2 in toluene, respectively. The Zr/Cr ratios were 1:1 and 2:1, respectively.

10

The results presented in Table 2 show that the catalyst Cp_2ZrBz_2 of Examples 10 to 13 has a highest activity with a Zr/Cr molar ratio of about 0.5:1. When this ratio is increased, the catalyst activity decreases and becomes zero at a ratio of 2:1. The

15 catalyst Cp_2ZrMe_2 shows a decreasing activity with increasing ratio Zr/Cr from 0.5:1 to 2:1. Thus, for both catalysts an optimal ratio seems to be Zr/Cr = 0.5:1.

20

25

30

35

TABLE 2
Polymerisation of ethylene in the presence of catalyst
Cr/silica + Cp₂ZrR₂ with various Zr/Cr molar ratios

Ex.	R, R''	Zr/Cr	H ₂ (bar)	Temp. (°C)	Activity g/g·h	MFR g/10 min	HLMFR g/10 min
Ex. 10	Bz	0,25	2	93	1115	0.087	16
Ex. 11	Bz	0,5	0.5	94	1656	0.088	13.75
Ex. 12	Bz	1	0.5	93.5	1282	0.034	7.93
Ex. 13	Bz	2	1	95.3	0	-	-
Ex. 14	Me	0,5	0.5	4	1174	0.029	6.02
Ex. 15	Me	1	0.5	94	970	0.014	4.06
Ex. 16	Me	2	0.5	93.6	525	0.021	4.63
Comp. 9		-	1	97	617	0,091	14,5

Examples 17 to 22

These examples demonstrate the effect of varying the partial pressure of hydrogen in the reactor when polymerising ethylene in the presence of catalysts Cp_2ZrBz_2 and Cp_2ZrMe_2 . In all examples the molar ratio Zr/Cr equalled 0.5:1. Polymerisation parameters and obtained results are given in Table 3.

Examples 17 to 20

Polymerisation catalyst: Cr/SiO₂ contacted with Cp_2ZrBz_2 .

The catalyst was prepared analogous to example 11 by suspending 1.501 g of reduced 1% by weight of Cr/SiO₂ in 12.473 g of mineral oil in a 50 ml glass bottle provided with a septum. To this mixture was added 0.603 ml of a 10% by weight solution of Cp_2ZrBz_2 in toluene and the mixture was stirred for another 1 h. The obtained catalyst was then used in the polymerisation of ethylene according to the general polymerisation procedure outlined above, with hydrogen pressures of 0, 0.5, 1 and 2 bars, respectively.

Examples 21 and 22

Example 14 was repeated, except that the hydrogen pressure was 1 bar and 2 bars, respectively.

The results presented in Table 3 show that catalyst Cp_2ZrBz_2 and catalyst Cp_2ZrMe_2 behave differently in the presence of hydrogen. Catalyst Cp_2ZrBz_2 , used in Examples 17 to 21 has a higher activity around 1 bar hydrogen pressure. Increased hydrogen level increases the melt index and lowers the density of the produced polyethylene, which indicates an increasing amount of short chain branching. Catalyst Cp_2ZrMe_2 , used in Examples 14, 21 and 22 responds very little to an increased hydrogen pressure.

TABLE 3

Polymerisation of ethylene in the presence of catalyst
Cr/silica + Cp₂ZrR₂ (Zr/Cr molar ratio 0.5) at increasing H₂ levels

Ex.	R, R"	H ₂ (bar)	Temp. (°C)	Activity g/g·h	MFR g/10 in	HLMFR g/10 min	Density g/cm ³
Ex. 17	Bz	0	92,8	923	0,06	8,9	0,937
Ex. 18	Bz	0,5	93	1290	0,15	19,8	0,937
Ex. 19	Bz	1	93,2	1413	0,2	28,2	0,934
Ex. 20	Bz	2	93	1057	1,07	87,6	0,928
Ex. 14	Me	0,5	94	1174	0,029	6,02	0,948
Ex. 21	Me	1	94	1190	0,021	5,89	0,948
Ex. 22	Me	2	94	948	0,034	8,93	0,946
Ex. 9		1	97	617	0,091	14,5	0,949

Example 23

Example 11 was repeated, except that the level of hydrogen was increased to 1 bar.

5 Example 24

Example 12 was repeated, except that the level of hydrogen was increased to 1 bar.

Polyethylenes produced with catalyst $\text{Cr/SiO}_2 + \text{Cp}_2\text{ZrBz}_2$ were
10 subjected to spectroscopic analysis of end groups with IR and
 ^{13}C -NMR. The spectroscopic analysis shows that the branches are
mainly ethyl and butyl branches which have been introduced by the
copolymerisation of 1-butene and 1-hexene as comonomers produced
from ethylene simultaneously with the polymerisation reaction in
15 the reactor. Obtained results are presented in Table 4.

The results of Table 4 show that there is produced a considerable
amount of short chain branching on the polyethylenes during
polymerisation. The short chain branching can be controlled by
20 using catalysts with different Zr/Cr ratios and by adjusting the
hydrogen level.

25

30

35

Table 4
Polymerization of ethylene in the presence of catalyst $\text{Cr/SiO}_2 + \text{Cp}_2\text{ZrBz}_2$

Ex.	Zr/Cr mol/mol	H ₂ (bar)	Temp. (°C)	MI g/10 min	Density g/10 min	Methyl ¹⁾ pr. 1000 c	Vinyl ¹⁾ pr. 1000 c	Trans ¹⁾²⁾ pr. 1000 c	Ethyl ³⁾ pr. 1000 c	Butyl ³⁾ pr. 1000 c
Ex. 11	0,5	0,5	94	0,09	0,945	4,2	0,89	0,016	2,0	1,7
Ex. 23	0,5	1	97	0,82	0,935	8,3	0,91	0,021	4,0	4,6
Ex. 12	1	0,5	93,5	0,03	0,94	3,7	0,81	0,02	2,4	1,8
Ex. 24	1	1	97	0,35	0,945	5,5	0,95	0,028	1,8	2,0
Comp. 9		1	97	0,09	0,949	1,3	0,87	0,002	0,3	0,3

1) From IR measurements

2) Transvinylene fragments

3) From ¹³C-NMR measurements




C l a i m s

1. A catalyst system for the polymerisation of ethylene,
5 comprising chromium oxide supported on an inorganic support,
characterised by:

- a) said support being a particulate inorganic oxide;
- b) the chromium of said chromium oxide being in a
reduced oxidation state,

10 and comprising

- c) a metallocene compound having the formula:



wherein Cp is an unsubstituted or substituted cyclopentadienyl
compound, and R' and R'', independant of each other, are selected
15 from the group comprising alkyls having 1 to 6 carbon atoms,
unsubstituted or substituted benzyl, and phenoxy substituted with
alkyls having 1 to 6 carbon atoms, and R' or R'' may be a halide.

2. A catalyst system according to claim 1, characterised in
20 that the cyclopentadienyl compound is substituted with radicals
selected from the group comprising unsubstituted and substituted
linear, branched, cyclic or partially cyclic alkyl radicals and
annelated cyclic radicals, containing 1 to 20 carbon atoms; un-
substituted and substituted monocyclic or polycyclic aryl
25 radicals which optionally also may contain hetero atoms; and
aralkyl radicals; the substituents on the cyclopentadienyl ring
may also form annelated structures comprising one or more fused
benzene, naphtalene or cyclohexene rings, which optionally may
contain hetero atoms, and the two cyclopentadienyl rings may also
30 be connected through a bridge.

3. A catalyst system according to claim 1, characterised in
that R' and R'' are selected from the group comprising chloride,
methyl, benzyl or phenoxyethyl, and combinations thereof.

35

4. A catalyst system according to claims 1 to 3, charac-
terised in that Cp is an unsubstituted cyclopentadienyl and that
R' and R'' are equal and are either methyl or benzyl.

5. A catalyst system according to claims 1 to 4, characterised in that the metallocene is bis-cyclopentadienyl-zirconium dibenzyl.
- 5 6. A catalyst system according to claim 1, characterised in that said support is a particulate, inorganic oxide selected from the group comprising alumina, silica, titania, zirconia, magnesia, and combinations thereof.
- 10 7. A catalyst system according to claim 6, characterised in that said support is silica having the shape of spherical or spheroidal particles with a particle size in the range of from 20 μm to 150 μm , and a surface area from 200 m^2/g to 600 m^2/g .
- 15 8. A catalyst system according to claim 1, characterised in that the chromium is present in an amount from 0.1 % to 10 % by weight calculated as metallic chromium based on the weight of the chromium/silica catalyst of a) and b).
- 20 9. A catalyst system according to claim 8, characterised in that the chromium is present in an amount from 0.5 to 2,0 % by weight of chromium.
10. A catalyst system according to claim 1 to 5, characterised
25 by a molar ratio between zirconium and chromium in the final catalyst in the range from 0.1:1 to not higher than 2:1.
11. A catalyst system according to claim 9, characterised in that said molar ratio between zirconium and chromium is from
30 0.5:1 to 1:1.
12. A method for the preparation of the catalyst system of claim 1, comprising the steps of:
- a) calcining a support being a particulate, inorganic
35 oxide selected from the group comprising alumina, silica, titania, zirconia, magnesia, and combinations thereof,
 - b) joining onto the surface of said support a chromium-organic compound to obtain a catalyst precursor,
 - c) subjecting said catalyst precursor to oxidising



/h

25

60848

PATENTSTYREI

08.APR98 981631

Sammendrag

Katalysator for polymerisasjon av etylen, omfattende en bærer av et partikkelformig uorganisk oksid som bærer et kromoksid hvor krom har et lavt oksidasjonstrinn, og en metallocenforbindelse med formelen $Cp_2ZrR'R''$, hvor Cp er en usubstituert eller substituert syklopentadienylforbindelse, og R' og R'' er valgt blant alkyler med 1-6 karbonatomer, usubstituert eller substituert benzyl, og fenoksy substituert med alkyler med 1-6 karbonatomer, og R' eller R'' kan være et halogenid. Det beskrives også en fremgangsmåte for fremstilling av katalysatoren.

